



NATIONAL TESTING LABORATORY PVT. LTD.

F.No. FO1 (5.10)

B-265, Mangolpuri Industrial Area, Phase-I, Delhi-110083
Ph. : 011-32469295, 27912990-93 (4 Lines), Tel/fax : 011-27912993
Email: ntl Delhi@yahoo.co.in, Visit us: www.nationaltestinglaboratory.net

Issued to:

M/s Hi-Tech International
Plot No. 99, IMT, Manesar
Gurgaon, Haryana

TEST-REPORT

Report No.:-160601GEN176524

Date of Report:-11/06/2016

Your Ref. No.:-Nil

Date of Receipt:-01/06/2016

Sample Description:-Dessicant Clay

S. No. Test

Test Method

Test Result

Requirement

Conformity

MIL D-3464-E

1. pH Value aq. extract
(5% Solution)

IS 2720(Pt-26):1987
Guideline

7.04

2. Electrical Conductivity of
the aq. extract, ms/cm
(5% Solution)

IS 2720(Pt-21):1977
Guideline

12.8

3. Mass Content of Water-Soluble
Substance, %

IS 2720(Pt-21):1977
Guideline

27.3

4. Particle Size % of Retained
½ Inch²
80 No.

MIL D-3464-E

0
99.7

0 Max.
96.0 Min.

Yes


5. Adsorption Capacity, gm
(at 25°C and 40% relative humidity)

MIL D-3464-E

7.35

6.0 Min.

Yes



KA

Lab Incharge

B. N. JHA

Quality Manager

Authorised Signatory

- (1) The results listed refer only to tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
- (2) Total liability of our Lab is limited to the invoiced amount.
- (3) Samples will be destroyed after 90 days from the date of test report unless otherwise specified.
- (4) This report is not to be reproduced wholly or in part and cannot be used as an evidence in the court of Law and should not be used in any advertising media without our special permission in writing
- (5) Report refer to the sample submitted to us and not drawn by us unless mentioned otherwise.